

THERMOBREAK[®] Solar

HIGH TEMPERATURE PIPE INSULATION FOR SOLAR HEATING



Thermobreak[®] Solar is a high temperature pipe insulation for solar water heating systems.

- Slide on
- UV Resistant
- 160°C Operating Temperature

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions

PHYSICALLY
CROSSLINKED
SEKISUI TECHNOLOGY

THERMOBREAK[®] Solar

TECHNICAL SPECIFICATIONS



Features

- Designed for long term outdoor exposure to high water temperatures encountered in solar heating.
- Heat bonded factory applied reinforced aluminium foil.
- Highly heat resistant internal layer.
- Flexible, tough and durable.
- Excellent compression resistance due to crosslinked foam structure.
- Superior insulating properties compared to other flexible closed cell foams.
- Superior UV resistance compared to PVC nitrile elastomeric foams.
- Contains up to 50% recycled content.
- No cladding required.

Size Availability

15mm wall thickness to fit all standard copper pipe diameters from 12.7mm (1/2") to 50mm (2").

For Other sizes and thicknesses, contact Sekisui Foam Australia.

(Other lengths available on request)

Distributed by

Thermobreak is a registered trademark of Sekisui Chemical Co. Ltd. or its subsidiaries.

Technical Data

Material:	Physically (irradiation) crosslinked closed cell polyolefin foam with factory applied reinforced aluminium foil and 6mm highly heat resistant internal layer
Density:	25kg/m ³ (foam only)
Thermal Conductivity: (ASTM C518)	0.035 W/mK (@ 23°C mean temperature)
Water Vapour Permeance: (ASTM E96) 12mm thickness	0.000195 µg/N.s
Permeability resistance factor:	µ>80,000
Resistance to Fungi & Mould: (ASTM G21)	Excellent
Ozone Resistance:	Excellent
UV Resistance: (ISO 4892.3; AS 3706.11)	Excellent
Operating Temperature:	-40°C to 160°C
Intermittent Temperature:	190°C

Flammability

AS 1530.3 (1999)
Spread of Flame Index: 0
Heat Evolved Index: 0
Ignitability Index: 0
Smoke Develop Index: 0-1

Compliance

Complies with the Building Code of Australia requirements under AS/NZS 4859.1, AS/NZS 3500.4, AS/NZS 1530.3.

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions



**Sekisui Foam Australia
Head Office**

1-5 Parraweena Rd, PO Box 2898,
Taren Point NSW 2229 Australia
Tel: +61 2 9525 9880
Fax: +61 2 9525 8004
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au

Queensland Branch

15/853 Nudgee Rd, PO Box 448,
Northgate QLD 4013 Australia
Tel: +61 7 3267 7100
Fax: +61 7 3267 7166
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au