

Staircase components



FEATURES

- Engineered solid hardwood with the look, feel and properties of traditional timber
- Sustainably sourced, VOC free, recyclable
- Secure supply chain, competitive pricing
- Uniform and consistent colour
- Allows the use of unique patch fittings
- Solid timber treads up to 480x240x2450mm, eliminating the need for lamination
- Proudly Australian made

NWW.CRAFTEDHARDWOODS.COM 1300 320 610

Staircase components



FINISH OPTIONS

Select your cut type. The unique engineered fold pattern and square dimensions means you can choose a cut that suits your application and finish.





QUARTER SAWN Modern look with clean linear finish. BACK SAWN

Rustic look with natural timber features exposed for character.

SPECIES TECHNICAL INFORMATION	Blackbutt	White Gum	Tasmanian Oak	
Density	950kg/m3	800kg/m3	770kg/m3	
Modulus of Elasticity (MOE)	20,680 Mpa	16,900 Mpa	16,030 Mpa	
Bending Strength (f'b) (MOR)	97 Mpa	94 Mpa	65 Mpa	
Janka hardness	7.6	5.7	4.4	
Stress Grade	F27	F17	F22	
Fire Group Number (AS/NZS 3837)	3	3	_	
Average Critical Heat Flux (kW/m2) (AS/ISO 9239.1)	4.8	3.8	_	
Char Rate (mm/min)	0.69	0.84	_	

SPAN TABLES

Span tables are provided for Blackbutt and Tasmanian Oak. Table 1 is the minimum thickness for a given span for residential and commercial applications and the loadings adopted are in accordance with Table 2.

TABLE 1 – STAIR TREADS CERTIFICATION	Stair width						
Species	750mm	1000mm	1200mm	1500mm	1800mm		
	Residential minimum thickness						
Blackbutt	26mm	32mm	38mm	48mm	58mm		
Tasmanian Oak	26mm	32mm	38mm	48mm	58mm		
	Commercial minimum thickness						
Blackbutt	28mm	34mm	40mm	50mm	60mm		
Tasmanian Oak	28mm	34mm	40mm	50mm	60mm		
TABLE 2 – LOADINGS FOR ALL SPECIES (AS1170.1 – Structural design actions)							
Occupancy	UDL (kPa)		PLL (kN)	Line L	Line Load (kN/m)		
Residential	2		2.7		2.2		
Commercial	4		4.5		2.2		