

How to specify:

Resin BOUND surface course consisting of aggregate particles, fully coated with chemically curing, UV stable, flexible, crystal clear resin, hand finished by trowel with a minimum 10 year guarantee, as supplied and laid by StoneSet Permeable Paving P/L or an approved agent, 15c, 390 Eastern Valley Way, Roseville, NSW. Contact: 1300 392155

The resin must also include a suitable adhesion agent to ensure complete adhesion with the aggregate and the setting time must be controlled by use of a catalyst so that the timing of the cure ensures; a) sufficient trowelling time, b) adequate but not excess drainage of the resin during curing to create a strong bond with the base and c) adequate time to allow the application of glass/sand dusting to ensure early life grip. The aggregate and resin must be thoroughly combined in a forced-action mixer immediately before spreading so that each aggregate particle is fully coated with resin before laying.

To specify the colour and texture:

Identify and name the Product Code, Description (including nominal size) and the depth of installation.

The final trowelled mixture should be permeable consistent with the predicted traffic.

FOR EXAMPLE

Product Code: S10010/02

Description: 3mm Beach

Layer thickness: 12mm

This information is available on the sample discs (Code and description) and use StoneSet construction advice to ascertain the correct layer thickness. If you require any technical information contact StoneSet technical sales on 1300 392155

